

For the information of Surveyors and the Committee only.

Received at

Office,

19

# Lloyd's Register of Shipping.

Order: 162895.

(Report on Machinery, No.

Port

No. 26597

## ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or castings~~, as herein described, manufactured by Messrs. Gutehoffnungshütte A.G. of Sterkrade

for the Engines No. being constructed by

of for the Ship No. 156, being built by Messrs. Kockums Mek.Verkstad of Malmö

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Malmö.

Forgings or Castings.

Lloyd's

Düsseldorf 3rd April 1928.

No. 272/273/274.

K.2.4.28.

F. Fohlsch

<del>PROPELLER SHAFT</del>	<del>PROPELLER SHAFT</del>	<del>INTERMEDIATE SHAFT</del>	TUBE SHAFT.
1 prop. shaft with brass liner <del>XXXXXXXXXXXX</del>	1 prop. shaft with brass liner	1 prop. shaft with brass liner	SCREW SHAFT.
272	273	274	
Annealed	Siemens	Martin	Ingot Steel
forged	forged	forged	
Yes	Yes	Yes	
261 mm ø	261 mm ø	261 mm ø	
rough	turned	and finished	
.798	3"	.798	3"
30,4	30,5	28,9	
33,3	33,0	32,0	
180 degr.good	180 degr.good	180 degr.good	
2.4.28.	2.4.28.	2.4.28.	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

any chargeable) £

To be paid at Düsseldorf.

wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

002109-002118-0201

499-570



# Lloyd's Register of Shipping

## ENGINE FORGINGS

to report that the forgings ~~xxxxxxx~~ as herein described, manufactured by Messrs. Gutehoffnungshütte A.G. of Sterkrade being supplied by the engines No. 156 being built by Messrs. Kockums Mek. Verkejsk for the ship No. 156 of Malmö.

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to the engines.

Düsseldorf 3rd April 1926.

*F. F. F.*

274/273/274.  
2.4.26.

TUBE SHAFT.


SCREW SHAFT.

xxxxxxx	xxxxxxx	xxxxxxx
1 prop. shaft with brass liner with brass liner	1 prop. shaft	1 prop. shaft
274	273	272
Annals	Stemens	Martin
forged	forged	forged
Yes	Yes	Yes
261 mm Ø	261 mm Ø	261 mm Ø
rough	turned	finished
3" 7.98	3" 7.98	3" 7.98
30.4	30.5	28.9
33.3	33.0	33.0
180 degt. good	180 degt. good	180 degt. good
2.4.26.	2.4.26.	2.4.26.

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:-

To be paid at Düsseldorf.

of steel, state whether made by the Open Hearth process.



© 2020  
Lloyd's Register  
Foundation