

For the information of Surveyors and the Committee only.

Received at

Office, 29 APR 1930 19

Lloyd's Register of Shipping.

(Report on Machinery, No. 41190 Port Stull)

No. 20877 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by The Rotherham Forge & Mill Co. of Rotherham for the Engines No. 1404 being constructed by Messrs C. D. Holmes & Co. Ltd. of Stull for the Ship No. _____, being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to _____

on Forgings or Castings.

R.W. Boomber

Sheffield 16/4/30

Lloyd's
No. 26
R.W.C. 8/4/30

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			SCREW SHAFT.
Material* ...	Premier Steel			
Made ...	Forged			
Annealed ...	Yes.			
Dimensions, Forgings	Dia $7\frac{1}{2}$ "			
Weight, Castings				
Press on Inspection	Black Forging			
Tests on Standard Test Pieces.	436.			
Ball Test—	29.4			
Stress per square inch ...	31.0			
Elongation per cent ...	180°			
Bending Test—				
Angle before fracture ...				
When Inspected	28/3/30 to 8/4/30.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £ /

To be paid at /

© 2020

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.