

Lloyd's Register of Shipping.

Order: 187303.

(Report on Vessel No. 20623 Port Hamburg)

No. 3900

SHIP FORGINGS ~~OR CASTINGS~~

I have to report that the undermentioned ~~XXXXXX~~ Steel Forgings ~~XX~~ ~~XXXXXX~~, manufactured by Messrs. Fried. Krupp A.G. of Essen for the Vessel No. 517, being built by Messrs. Germaniawerft A.G. of Kiel-Gaarden have been inspected by me as set forth below and found to be, so far as can be seen, 1 intermediate post and 1 rudder shaft sound and free from surface defects.-

in Forgings or Castings.

Lloyd's

Düsseldorf 23rd January 1932.

No. 349/352.

L. 22.1.32.

J. Höger

	349 1 interm. post XXXXXX	352 1 rudder shaft XXXXXX	STEM.
Material*	Annealed Siemens-Martin Ingot Steel		
made	forged		
lealed	Yes		
ensions	265 mm Ø	295 mm Ø	
ess on Inspection	rough turned	and finished	
when Inspected	22.1.32.	22.1.32.	
CASTINGS.	.798	.798	3"
s on Standard Test Pieces.			
le Test—			
ns per square inch	29,5	29,0	30,7
tension per cent. ...	27,6	33,2	32,8
Bending Test—			
ngle before fracture	180 degr. good	180 degr. good	
Test—			
ight from ground ...			
nering Test—			
made according to Rules and found satisfactory ...			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £

To be paid at **Düsseldorf.**

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

9. T.



002385-002400-0168