

SSEL'S NAME

BALTKON

Report

CARDIFF

No. 56114

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in *hundredths* of an inch.

20 MAY 1943


20 MAY 1954

or in inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.	
	Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.			
	Port.	Std.	Port.	Std.			Port.	Std.	Port.	Std.			Port.	Std.	Port.	Std.	Port.	Std.		
GE SHEER STRAKE	48	48	46										32	29	27				Circled plate now renewed. Adjacent plates drilled and found satisfactory	
e below	48	47	47										32	27	28					
R STRAKE	48	46	47			46	56	49					40	41	42					
ake below	48	45	49			56	54	56					40	41	42					
"	48	43	47			56	47	54					40	39	36					
"	48	45	53			56	52	55					40	38	28				The upper strakes H&T of shell plating (P+S) forward have apparently been renewed recently from stem to 1/2 L forward. ✓	
"						56	34	49	22				40	35	36					
"																				
"																				
"																				
"																				
"																				
"																				
"																				
"																				

Drillings at ends to be made in the vicinity of the peak bulkheads.

002449-002456-0024



© 2020

Lloyd's Register Foundation