

SSEL'S NAME *U.S. ELPIS*Report *PIRAEUS* No. *5314*

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in $\frac{745}{100}$ of an inch.*4.5.1948*

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
R SHEER STRAKE																			
Deck Focle. <i>see below</i>	K	32	32	32	.	.	32	32	32	.	.								
IN SHEER STRAKE	J	58	50	56	8	2	40	40	40	.	.	40	40	40	.	.			
Strake below	H	48	45	44	3	4	40	40	40	.	.	40	38	40	2	.			
" "	G	48	45	45	3	3	40	35	40	5	.	40	40	40	.	.			
" "	F	48	44	44	4	4	40	37	40	3	.	40	40	40	.	.			
" "	E	50	40	43	10	7	42	38	38	4	4	42	38	38	4	4			
" "	D	54	46	46	8	8	44	34	38	10	6	44	40	44	4	.			
" "	C	54	53	53	1	1	44	34	34	10	10	44	40	40	4	4			
" "	B	54	50	46	4	8	44	36	34	8	10	44	38	38	6	6			
" "	A	54	53	53	1	1	44	38	44	6	.	44	37	39	7	5			
KEEL		74	65		9		56	45		11		56	50		6				

O = Revised

© 2020

Lloyd's Register Foundation

Drillings at ends to be made in the vicinity of the peak bulkheads.

002701-002710-0030