

VESSEL'S NAME

Eso Hull

REPORT

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.	
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.			
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		
EDGE SHEER STRAKE																	
Edge Strake below																	
DEER STRAKE	L	107	95	99	12	8	103	83	79			103	75	75	28	28	
Strake below	K	83	71	67	12	16	83	63*	69			83	61*	63*	22	20	
"	J						67	41*	55								
"	J	67	57	57	10	10	67	45*	49*			67	51*	57	16	10	
"	H	67	59	57	8	10	67	47*	47*			67	51*	61	16	6	* Plates required
"	G	67	59	63	8	4	67	63	57			67	57	57	10	10	
"	F	75	71	63	4	12	75	65	65			75	71	65	4	10	
"	E	75	71	67	4	8	75	71	67			75	63	65	12	10	
"	D	75	55*	59	20	16	75	73	73			75	53*	67	22	8	
"	C	75	59	51*	16	24	75	53*	55*			75	55*	53*	20	22	
"	B	75	59	59	16	16	75	53*	55*			75	55*	53*	20	22	
"	A	75	55*	51*	20	24	75	55*	53*			75	55*	53*	20	20	
"	Keel	107	87		20		107	107				107	103		4		

Drillings at ends to be made in the vicinity of the peak bulkheads.

2021  
202736-002740-0280  
Lloyd's Register Foundation