'S NAME S.S. "ISONZO" Report Trieste No. 13017

ICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in ~~[illegible]~~ mm

RAKE.	AMIDSHIP. Original Thickness.	Thickness by drilling. Port.	Thickness by drilling. Std.	Diminution if any. Port.	Diminution if any. Std.	FORWARD. Original Thickness.	Thickness by drilling. Port.	Thickness by drilling. Std.	Diminution if any. Port.	Diminution if any. Std.	AFT. Original Thickness.	Thickness by drilling. Port.	Thickness by drilling. Std.	Diminution if any. Port.	Diminution if any. Std.	REMARKS.
EER STRAKE...																
w.....																
AKE	22	22	22	–	–	12	12	12	–	–	12	12	12	–	–	
elow	19	19	19	–	–	12	12	12	–	–	12	12	10.5	–	1.5	
"	16.5	14.5	15	2	1.5	12	12	12	–	–	12	12	12	–	–	Forward
"	16.5	14.5	16	2	.5	12	9½	10	2½	2	12	11	11	1	1	Port Stb.
"	16.5	15	15	1.5	1.5	12	11	6.5	1	5.5	12	10.5	9.5	1.5	2.5	1 plate renewed / 1 plate renewed
"	16.5	16.5	16	–	.5	12	7	6.5	5	5.5	12	10.5	10	1.5	2	1 " " / 2 plates "
"						12.5	7	6.5	6	5.5	12.5	10.5	10	1.5	2	2 plates " / 3 " "
"																
"																
"																
"																
"																
"																

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020 Lloyd's Register Foundation

002825-002829-0011

carried out. Witness