

by chargeable) & Board

of front plates at bottom 215

# Register in Shipping.

## RESULTS OF TESTS OF STEEL.

Made by Messrs John Brown & Co., Sheffield.

For Messrs John Brown & Co. Clydebank. Engine No 597

have to report that the Iron or Steel Castings or Castings, as herein described, manufactured by **Carroll Steel Cast Co.** of **Liverpool**

Date of Test.	Batch No.	Test No.	Chemical Mark	Thickness	Breadth	Area	Tons, Total.	Tons per square inch.	Extension in 3" ins. %	Bend
1. IP Wheel		2573	✓	✓	✓	✓	✓	38.0	25	180°
1. " "		2574	✓	✓	✓	✓	✓	38.0	25	"
1. " "		2575	✓	✓	✓	✓	✓	38.0	25	"
1. IP Astern Wheel		2551	✓	✓	✓	✓	✓	37.2	25.5	"
1. IP Ahead " "		2566	✓	✓	✓	✓	✓	37.6	26	"
1. " " "		2567	✓	✓	✓	✓	✓	37.6	26	"
1. " " "		2578	✓	✓	✓	✓	✓	38.0	25	"
1. " " "		2579	✓	✓	✓	✓	✓	38.6	26	"
1. " " "		2581	✓	✓	✓	✓	✓	38.6	25	"
1. " " "		2560	✓	✓	✓	✓	✓	35.6	28	"
1. " " "		2582	✓	✓	✓	✓	✓	38.6	25	"
1. " " "		2583	✓	✓	✓	✓	✓	38.6	25	"
1. L.P. Astern Wheel		2521	✓	✓	✓	✓	✓	35.2	27.0	"
1. " " "		2523	✓	✓	✓	✓	✓	37.8	25.5	"
1. L.P. Ahead Wheel		2831	✓	✓	✓	✓	✓	38.0	24	"
1. " " "		2548	✓	✓	✓	✓	✓	34.6	28	"
1. " " "		2546	✓	✓	✓	✓	✓	34.6	28	"
1. " " "		2544	✓	✓	✓	✓	✓	37.2	27	"
1. " " "		2542	✓	✓	✓	✓	✓	37.2	27	"
1. " " "		2824	✓	✓	✓	✓	✓	36.4	28	"
1. " " "		2537	✓	✓	✓	✓	✓	35.2	27	"
1. " " "		2535	✓	✓	✓	✓	✓	37.4	28	"
1. " " "		2533	✓	✓	✓	✓	✓	37.4	28	"
1. " " "		2820	✓	✓	✓	✓	✓	38.5	26.5	"
1. " " "		2818	✓	✓	✓	✓	✓	38.5	26.5	"
1. " " "		2819	✓	✓	✓	✓	✓	38.5	26.5	"

W. G. Hume

25 MAY 1920

002838-002845-0028




Lloyd's Register Foundation

EIGHT OF BLADES. DIAMETER AT TIP. NO. OF ROWS.

John Brown & Co. Ltd.

By debit

2597



© 2020

Lloyd's Register  
Foundation