

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19__

Lloyd's Register of Shipping.

(Report on Machinery, No. 9514 Port Gothenburg)

ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured

Messrs. Dortmunder Union of Dortmunder

the Engines No. _____ being constructed by Messrs. A.-B. Götaverken

Gothenburg for the Ship No. 476, being built by

Messrs. A.-B. Götaverken of Gothenburg

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Gothenburg.

Gothenburg, 29th September, 1933,

14882 14883-14887/14889
25.8.33 EB 25.8.33.

E. Bernelius


	XXXXXXXXXX 1 thrust shaft.	XXXXXXXXXX 2 intermediate shafts.	XXXXXXXXXX 2 intermediate shafts.	XXXXXXXXXX 2 interm. shafts.
Material	14882 Annealed	14883/14884 Siemens	14885/14886 Martin	14887/14889 Ingot Steel.
Condition	forged	forged	forged	forged
Sound	Yes	Yes	Yes	Yes
Diameter	Diam. 260 mm.	Diam. 245 mm.	Diam. 245 mm.	Diam. 245 mm.
Surface	Rough turned and finished.			
Surface Finish	.798 3"	.798 3"	.798 3"	.798 3"
Weight	29.1	29.6 32.0	29.2 31.4	30.2 30.5
Strength	35.0	28.0 25.4	30.6 32.0	30.6 30.6
Test	180° good.	180° good.	180° good.	180° good.
Inspected	25.4.33. 16.8.33	25.4.33 25.8.33	25.4.33 25.8.33	25.4.33 25.8.33

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(chargeable) £ —

To be paid at — 004 —

Light iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



002947-002955-0087

THE SURVEYORS ARE REQUESTED NOT TO WRITE ACROSS THIS MARGIN.