

Lloyd's Register of Shipping.

(Report on Machinery, No. 17504 Port Antwerp)

No. 2808 ENGINE FORGINGS ~~OR CASTINGS~~.

The words FORGINGS or CASTINGS should be struck out as may be required.

We have to report that the Forgings or Castings, as herein described, manufactured by Waino Anglo-Franco Belge of La Croisette for the Engines No. _____ being constructed by Waino Carolo of Gand for the Ship No. 550 & 551, being built by Messrs Scott's S. B. & Co of Glasgow have been inspected by us as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Gand.

Mark on Forgings ~~Castings~~.

AB

Lloyd's
No. 2808
AB 24-4-30

W.A. Black. & A. Bennett.
Antwerp.

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	4 Connecting Rods (2 to each test)			
	FLYWHEEL SHAFT.			SCREW SHAFT.
Material*	S.M. Steel			
How made	Forged			
If Annealed	Annealed			
Dimensions, Forgings	175 mm dia			
Weight, Castings				
Progress on Inspection	Rough turned			
Tests on Standard Test Pieces.				
Tensile Test— Tons per square inch	53	52.5		
Extension per cent	25.5	25.5		
Cold Bending Test— Angle before fracture	180° without fracture			
Dates when Inspected	Feb 17, Apr 2nd & 24th 1930.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at

© 2020
Antwerp.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.