

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19\_\_

# Lloyd's Register of Shipping.

(Report on Machinery, No. 17504 Port Ant)

## No. 4589 ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by Usines Anglo-Franco-Belg. of La Croix for the Engines No.  being constructed by Usines Card of Gaud for the Ships No. 5504551, being built by Messrs Scotts, S.B. & Eng. Co. Ltd. of Gretnock have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Gaud.

on Forgings ~~or Castings~~.

M.A. Black.  
- Antwerp.

Lloyd's  
No. 4589  
MAB. 17-2-30.


	CRANK SHAFT.	<del>THRUST SHAFT.</del>	INTERMEDIATE SHAFT.	TUBE SHAFT.
	8. Connecting Rods	(2 Connecting Rods to each test.)		
	FLYWHEEL SHAFT.		M.A.B.	SCREW SHAFT.
Material	8. In. Steel	/		
Made	Forged.			
Heat treated	Yes.			
Dimensions, Forgings	125 <sup>1/2</sup> dia			
Material, Castings	<input checked="" type="checkbox"/>			
Finish on inspection	Rough turned.			
Tests on Standard Test Pieces.				
Yield Test—	46 <sup>5</sup> , 52 <sup>6</sup> , 45 <sup>8</sup> , 54 <sup>7</sup>			
Extension per square inch	32, 29 <sup>3</sup> , 32, 30 <sup>7</sup>			
Bending Test—	all 180° Solid without fracture.			
Time before fracture	9/1/30, 17/2/30, 30/1/30			
When Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2020

Antwerp  
Lloyd's Register  
Foundation

003138-003146-0123