

For the information of Surveyors and the Committee only.

Received at

Office,

19

Lloyd's Register of British & Foreign Shipping.

(Report on Machinery, No. *35686* Port *GLASGOW*)

No. *4044*. ENGINE FORGINGS OR CASTINGS.

I have to report that the Iron ~~or Steel~~ Forgings ~~or Castings~~, as herein described,
manufactured by *Fife Forge Co.* of *Kirkcaldy*
for the Engines No. *450* being constructed by *Liepmann & Co.*
of *Glasgow* for the Ship No. —, being built by
of —

have been inspected by me as set forth below, and found to be, so far as can
be seen, *sound*

Mark Forgings only

L. N. Lake

with

Lloyd's

No. *4040*

G.A.H.

CRANK SHAFT.

STRAIGHT SHAFTING.


THRUST SHAFT.

INTERMEDIATE SHAFTS.

PROPELLER SHAFT.

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
al° ...	<i>5 in 3 1/2 in</i>	<i>5 in 3 1/2 in</i>		<i>5 in 3 1/2 in</i>
made ...	<i>Forged</i>	<i>Forged</i>		<i>Forged</i>
sions ...	<i>6 3/4</i>	<i>6 3/4</i>		<i>7 1/2</i>
ss on { pection }	<i>Black</i>	<i>Black</i>		<i>Black</i>
on Standard est Pieces.				
e Test—	<i>31.0 31.0</i>	<i>29.0</i>		—
per square inch ...	<i>30.0 31.0</i>	<i>30.0</i>		—
ension per cent	<i>180° sound</i>	<i>180° sound</i>		—
bending Test—				
le before fracture ...	<i>9/4 6 20/4/15</i>	<i>14/6 1 18/6/15</i>		<i>26/3/15</i>
when Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—



Fee (if any chargeable) £

To be paid at

If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.


T.

Survey Fee

When applied for,

191

Thack Sept No 35686



© 2020

Lloyd's Register
Foundation

003162-003174-0028

