

156

6. For the information of Surveyors and the Committee only.

Received at Trieste Office, 17/3/25 1925

Lloyd's Register of Shipping.

Order: 259207St.
Post: 2916.

(Report on Vessel No. 7237 Port TRIESTE)

No. 1430. SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned ~~Iron or~~ Steel ~~Forgings or~~ Castings, manufactured by Messrs. Witkow, Bergb. & Eisenh. Gewerkschaft of Witkowitz for the Vessel No. 157, being built by Messrs. Cant. Navale Triestino of Monfalcone have been inspected by me as set forth below and found to be, so far as can be seen, 1 cast stern frame in 2 parts, sound and free from defects.

Mark on ~~Forgings or~~ Castings.

Lloyd's
No. 1430. 20/21.
JFR. 19.2.25.
Vienna, 16th March 1925.
for Mr. J. F. Robertson.
Hans Kollow.

	STERN FRAME. <u>Top</u>	BUDGET STERN FRAME <u>Keel.</u>	STEM.
Material*	Annealed Siemens	Martin Steel.	
How made	cast	cast	
Dimensions	to sketch	to sketch	
Progress on Inspection	almost finished	almost finished	
Date when Inspected	29.1; 19.2.25.	29.1; 19.2.25.	
CASTINGS.	No: 20.	21.	
Tests on Standard Test Pieces.			
Tensile Test—			
Tons per square inch	28.1 35.4	28.0 35.6	28.3 34.2
Extension per cent. 3"	35.5	36.2	36.2
Cold Bending Test—			
Angle before fracture	120 degr. good.	120 degr. good.	
Drop Test—			
Height from ground ...	10'	9'	
Hammering Test—			
If made according to Rules and found satisfactory ...	satisfactory	satisfactory	

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £
To be paid at VIENNA

17. MAR 1925



© 2020

Lloyd's Register Foundation

* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

2m, 12, 17. T

003357-003368-0188