

7. For the information of Surveyors and the Committee only.

Received at

Office

31 MAR 1930

19

Lloyd's Register of Shipping.

(Report on Machinery, No. 41176. Port Hull.)

No. 20622 ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by The Rotherham Forge & R. Mills Ltd of Rotherham for the Engines No. 1400 being constructed by Messrs C. D. Holmes & Co Ltd of Hull for the Ship No. _____, being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to _____

Forgings or Castings.

Lloyd's

No. as below
R.N.F. 21/3/30

R.W. Rawcett

Sheffield

26/3/30


	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.		3. <u>Con. Rods</u>	1. <u>SCREW SHAFT.</u>
1* ...			<u>Premiers</u>	<u>Steel</u>
ide ...			<u>Forged</u>	
aled ...			<u>Yes</u>	
ons, Forgings				<u>Dia 8 3/4"</u>
Castings			<u>Black</u>	<u>Forgings</u>
s on } ction }			<u>414</u>	<u>R3487</u>
n Standard t Pieces.			<u>31.8</u>	<u>413</u>
Test— er square inch			<u>32.0</u>	<u>31.4</u>
ion per cent			<u>180°</u>	<u>180°</u>
nding Test— before fracture				
hen Inspected			<u>19/3/30 to 21/3/30</u>	<u>14/3/30 to 21/3/30</u>

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £ ✓

To be paid at ✓

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2020

Lloyd's Register
Foundation

003357-003368-0271