

mag

NAME

"Ultramarino"

Report Baltimore

No. 8759

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.
decimal

The thicknesses are in / of an inch.

STRAKE	AMIDSHIP.				FORWARD.				AFT.				REMARKS.			
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.		Std.	Port.	Std.
DECK STRAKE	.60	.60			.38	.38			.36	.34						original thickness not known
LOW	.55	.55			.38	.38			.34	.34						
DECK STRAKE K	.55	.55			.48	.44			.46	.46						
below J	.56	.58			.46	.44			.46	.48						
H	.56	.54			.50	.48			.45	.46						
G	.64	.56			.56	.56			.54	.64						
F	.52	.48			.56	.56			.62	.58						
E	.60	.62			cement				.48	.60						
D									.62	.64						
									-	-						

Drillings at ends to be made in the vicinity of the peak bulkheads.

Drillings as of December 1945

003503-003512-0123

© 2020

Lloyd's Register
Foundation