

For the information of Surveyors and the Committee only.

Received at

Office,

19

Lloyd's Register of Shipping.

(Report on Machinery, No. 5952 Port Hongkong)

No. ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel Forgings or Castings~~, as herein described, manufactured by The Darlington Forge Ltd of Darlington for the Engines No. 619 being constructed for the Hongkong Whampoa Dock Co of for the Ship No., being built by

have been inspected by me as set forth below, and found to be, so far as can be seen, Sound.

To the order of Jas Morrison & Co Ltd, London

Forgings or Castings.

Lloyd's

No. 619
MR

M. Robertson

Darlington No. 619

3 Head End Rods

	CRANK SHAFT.	THRUST SHAFT.	STRAIGHT SHAFTING.	
			INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
<u>3 Cou Rods</u>	<u>Siemens Martin</u>	<u>Forged</u>	<u>Forged</u>	<u>Forged</u>
<u>1* ...</u>	<u>4" dia</u>	<u>8" dia</u>	<u>3 1/4" dia</u>	<u>5" dia</u>
<u>ade ...</u>	<u>Forging and testing</u>			
<u>ions ...</u>				
<u>s on } ection }</u>				
<u>on Standard st Pieces.</u>				
<u>Test— per square inch</u>	<u>38-735A29 30-0</u>	<u>34-2 31-8</u>	<u>39-2A-28-6</u>	
<u>tion per cent</u>	<u>34-32-0</u>	<u>33-0</u>	<u>35-0</u>	
<u>ending Test— before fracture</u>	<u>180-180</u>	<u>180</u>	<u>180</u>	
<u>When Inspected</u>	<u>13-6</u>	<u>14-6</u>	<u>24-6</u>	<u>26</u>


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any) chargeable) £ 3. 15. 0

To be paid at Darlington

If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

T.



© 2020

Lloyd's Register
Foundation

003503-003512-0223

Diameter of Safety Valve

Pressure to which each is adjusted

Is Easing