

For the information of Surveyors and the Committee only.

Received at **HULL** Office, **29 APR 1929** 19

# Lloyd's Register of Shipping.

(Report on Machinery, No. **40373** Port **Hull**)

## No. 17401 ENGINE FORGINGS ~~OR CASTINGS.~~

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by **The Rotherham Forge & R. Mills Ltd. of Rotherham.** for the Engines No. **587/8** being constructed by **Messrs Amos & Smith Ltd.** of **Hull** for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

to on Forgings ~~or Castings~~.

**R. W. Fawcett**

**Sheffield**

**13/4/29**

Lloyd's

No. **✓**

**R.N.F. 4/4/29.**

~~CRANK SHAFT.~~

**2. Cr. Rods.**

~~FLYWHEEL SHAFT.~~

~~THRUST SHAFT.~~

~~INTERMEDIATE SHAFT.~~

~~TUBE SHAFT.~~

~~SCREW SHAFT.~~

Material\* ...

**Siemens Steel**

made ...

**Forged**

annealed ...

**Yes**

ensions, Forgings

ight, Castings

gress on }  
Inspection }

**Black Forgings**

ests on Standard  
Test Pieces.

**652.**

nsile Test—

**29.0**

Tons per square inch

**35.0**

Extension per cent

**180°**

d Bending Test—

Angle before fracture

tes when Inspected


**28/3/29 to 4/4/29**

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £ **✓**

To be paid at **✓**

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2020

Lloyd's Register  
Foundation

003541-003548-0072

003541-003548-0073