

"RIA DE EL FERROL" Barcelona Report Nº 5220

THICKNESSES OF PLATING ascertained by drillings, and comparison of same with original thickness

The ticknesses are in m/m

STRAKE	AMIDSHIPS						FORWARD						AFT					
	Orig. thickness.	Thickness by drill. Port.	Thickness by drill. Starb.	Diminution if any Port, Starb.		Orig. thickness.	Thickness by drill. Port.	Thickness by drill. Starb.	Diminution if any Port, Starb.		Orig. thickness.	Thickness by drill. Port.	Thickness by drill. Starb.	Diminution if any Port, Starb.				
Star Sheer Strake,	12.5	12	12.5	.5	-	10	10	10	-	-	7	7	8	-	-			
Strake below	12.5	12.5	12.5	-	-	10	10	10.5	-	-	10	10.5	10.5	-	-			
in Sheer Strake	12.5	14	11.5	-	1	10	11	10.5	-	-	10	11	8	-	2			
Star Strake below	12.5	11.5	11	1	1.5	18.5	19	19	-	-	10	9.5	9	.5	1			
Star " "	12.5	13.5	13	-	-	18.5	18	18	.5	.5	10	10	10	-	-			
Star " Bilge	13.5	13	12.5	.5	1	18.5	15.5	17	3	1.5	10	9.5	8	.5	2			
Star " "	13.5					18.5	15	15	3.5	3.5	10	11	10	-	-			
Star " "	12.5					10	12	11	-	-	10	10.5	13	-	-			
Star " "	12.5					10					10							
Star plate	19.5					14.5					14.5							

REMARKS.-

The original thicknesses have been taken from shell expansion plan

The drillings have been made 2 frames spaces fore and aft from collision and after peak bulkheads respectively.

© 2020
Lloyd's Foundation

Lloyd's Register
Foundation

003679-003686-0216