

LETIZIA MONTANARI

REPORT

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

Original thickness	AMIDSHIP.				FORWARD.				AFT.				REMARKS.		
	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.			Diminution if any.	
	Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.		Port.	Std.
					46		FORECASTLE SIDES	42		POOP SIDES.				DECK PLTG.	
					46			46						FROM WITHIN POOP	
00					46			46						TO 1/2 L FWD:	
77					48			48						STRINGER 82	
64					48			48						ADJACENT STR. 76	
64					48			48						REMAINDER 66	
64					-			-							
76					87			52							
76					87			52							
76					87			52							
76					87			52							
76					87			86							
100					100										

Office Copy
 Sub AMM.
 23-6-55

Drillings at ends to be made in the vicinity of the peak bulkheads.

003706-003711-0280
 003711-0281

TEL: LONDON WALL 1234. TELEX: LONDON WALL 2485



© 2020

Lloyd's Register Foundation