

No 6062

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL FORGINGS.

de by Messrs John Brown & Co, Sheffield

Messrs John Brown & Co, Clydesbank. Enginee No 598.

Batch No.	Test No.	Charge Mark	Thickness	Breadth.	Area.	Tensile, Tons	Tons per square inch.	Extension in ins. %	Bend
cl	2563	v	v	v	v	v	37.6	26.0	180°
	2584	v	v	v	v	v	38.6	25.0	"
"	2565	v	v	v	v	v	37.6	26.0	"
Wheel	2552	v	v	v	v	v	37.2	25.5	4
l "	2553	v	v	v	v	v	37.2	24.5	4
"	2591	v	v	v	v	v	38.1	26.5	"
"	2570	v	v	v	v	v	38.0	25.0	"
"	2586	v	v	v	v	v	36.2	29.0	"
"	2571	v	v	v	v	v	38.0	25.0	"
"	2568	v	v	v	v	v	38.0	25.0	"
4	2588	v	v	v	v	v	36.2	29.0	"
"	2593	v	v	v	v	v	38.1	26.5	"
Wheel	2524	v	v	v	v	v	35.6	26.0	-
"	2527	v	v	v	v	v	37.2	25.5	"
Wheel	2849	v	v	v	v	v	35.6	27.0	"
4	2830	v	v	v	v	v	38.0	24.0	"
"	2829	v	v	v	v	v	38.8	26.0	"
"	2828	v	v	v	v	v	38.8	26.0	"
"	2827	v	v	v	v	v	38.8	26.0	"
"	2825	v	v	v	v	v	36.4	28.0	"
"	2843	v	v	v	v	v	36.2	24.0	"
4	2823	v	v	v	v	v	36.4	28.0	"
"	2822	v	v	v	v	v	36.4	28.0	"
"	2821	v	v	v	v	v	38.5	26.5	"
"	2838	v	v	v	v	v	36.4	25.0	"
"	2836	v	v	v	v	v	35.2	28.0	"
"	2834	v	v	v	v	v	35.2	28.0	"

J Brugle

W G Hume

© 2021

Lloyd's Register
Foundation

003712-003719-0084