

22 JAN 1948

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

## No. F2029 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by THE FIFE FORGE CO. LTD.

of KIRKCALDY  
for the ORDER Engines No. 2806 ORDERED by Messrs. A. Weir & Co. Ltd.  
of London FOR SAM VESSEL being constructed by \_\_\_\_\_ for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to % Grayson, Rollo & Glover Dock Ltd. Birkirkhead

Mark on Forgings or Castings.

Lloyd's  
No. 2029  
25-11-47.

Wm. A. Leggat

Leith 21 JAN 1948

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			No 2029
Material* ...				1- SCREW SHAFT WITH CONT. LINER
How made ...				S.M. Ingat Steel
If Annealed...				Forged
Dimensions				15 3/8" Dia
Weight } Forgings				113 cwt, 9 lb, 0 lb.
Weight, Castings ...				
Progress on } Inspection				Finish Machine
TEST RESULTS.				
Ultimate Tensile.				31.6
Tons per sq. in. ...				-
Yield Point.				30
Tons per sq. in. ...				-
Extension per cent				180
on 3 inches ...				4-11-47 — 25-11-47
Red. of Area % ...				
Cold Bending Test...				
Dates when Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £4-8-3<sup>d</sup>.

To be paid at

LEITH MONTHLY AG

© 2020

Lloyd's Register

Foundation

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

10m, 11.30. (MADE AND PRINTED IN ENGLAND)

003150-003762-0206