

7. For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19

Lloyd's Register of Shipping.

Order: 741
Best: 252 9 P (Report on Machinery, No. *8959* Port *Gothenburg*)

No *2536* ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by *Messrs. Borsigwerk, A.G.* of *Borsigwerk* for the Engines No. *961* being constructed by *Messrs. Götawerken A.B.* of *Göteborg* for the Ship No. *452335*, being built by *Caledon S.B. & Eng. Co. Ltd.* of *Dundee* have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to *Messrs. Götawerken, A.B. of Göteborg*

Forgings ~~or Castings~~

Vienna, 16th August 1930

Lloyd's
No. *4302*
S.15.8.30

590/91

of tender

W. Weiden

	FORGINGS 1 prop. shaft	CASTINGS 1 nut	INTERMEDIATE SHAFT.	TUBE SHAFT. SCREW SHAFT.
Material	Siemens Martin	Ingot Steel		
Condition	forged	forged		
Heat Treatment	annealed			
Dimensions, Forgings	290 ø	375 ø		
Castings	- - -	- - -		
Surface Condition	finished	finished		
Conformity to Standard	No: 590	No: 591		
Test—				
Per square inch	31.2	29.7		
Elongation per cent	76mm 27.6	33.5		
Hardening Test—				
Before fracture	180 degrees good			
When Inspected	8.8.; 15.8.30	8.8.; 15.8.30		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

of any chargeable) £ To be paid at _____
of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

© 2020

VIENNA

Lloyd's Register

Foundation

004055-004061-0216