

For the information of Surveyors and the Committee only.

Received at

Office,

10

Lloyd's Register of Shipping.

Order: 741

Best: 252 9 P

(Report on Machinery, No. 8259

Port

Göteborg

No. 2537

ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or Castings~~ as herein described, manufactured by Messrs. Borsigwerk, A.G., of Borsigwerk for the Engines No. ¹⁹⁶¹₉₆₂ being constructed by Messrs. Götawerken A.B. of Göteborg for the Ship No. 452 335, being built by Caledon S.B. & Eng. Co. Ltd of Dundee, have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Messrs. A.B. Götawerken, of Göteborg.

Forgings ~~or Castings~~

Vienna, 16th August 1930

Lloyd's

No. 4303

592/93

S. 15.8.30

Spare

H. Schneider

	CRANK SHAFT	THRUST SHAFT	INTERMEDIATE SHAFT.	TUBE SHAFT.
	1 propell. shaft	1 nut		
	SCREW SHAFT			SCREW SHAFT.
...	Siemens Martin Ingot Steel			
le ...	forged	forged		
ed ...	annealed			
ns, Forgings	290 Ø	375 Ø		
Castings	---	---		
on {	finished	finished		
tion {	No: 592/93x	No: 593		
a Standard				
Pieces.				
Test—	30.9	29.7		
r square inch				
in per cent	76mm 28.9	33.5		
ding Test—				
efore fracture	180 degrees good			
en Inspected	8.8.; 15.8.30	8.8.; 15.8.30		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

any chargeable) £

To be paid at

VIENNA

If wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

004055-004061-0218

Can the internal surfaces of the receivers be examined and cleaned?

24350 liters each

450%