

EL'S NAME S.S. "SHUN FUNG" ex "Tung Song" REPORT Hong Kong No. 12970

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.	
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.			
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		
DGESHEER STRAKE	H	40	40	35	-	5	24	37	40	-	-	24	42	42	-	-	
ge Strake below	G	32	35	32	-	-	32	35	40	-	-	32	32	32	-	-	
ER STRAKE	F	52	43	42	9	10	42	40	35	2	7	38	40	35	-	3	
Strake below	E	40	38	40	2	-	32	45	40	-	-	32	30	32	2	-	
Turn of Bilge		35	30	38	5	-	32	40	40	-	-	30	30	28	-	2	
	C	36	38	30	-	6	34	40	32	-	2	34	30	35	4	-	
	B	36	30	30	6	6	36	40	40	-	-	34	30	30	4	4	
	A	42	32	40	10	2	42	40	40	2	2	40	30	30	10	10	
KEEL	44	-	-				Decks Amidships					44	-	-			
							Stringer										
						Orig	Port	Stbd	Orig	Port	Stbd						
	Upper			Ford		.35	-	.32	.30	.30	.27			.26			
				Aft		.25	-	.22	.21	.24	.20			.22			
	Main			Ford		.40	-	.35	.36	.35	.35			.32			
				Aft		.42	-	.40	.36	.34	.30			.32			

Drillings at ends to be made in the vicinity of the peak bulkheads.

004213-004221-0219

James A. Anderson.