

VESSEL'S NAME CASTILLO MONTJUICH Report No.                     

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in  $\frac{1}{100}$  of an inch.

STRAKE	AMIDSHIP						FORWARD						AFT.						REMARKS.
	Original Thick- ness.	Thickness by drilling.		Diminution if any.		Original Thick- ness.	Thickness by drilling		Diminution if any.		Original Thick- ness.	Thickness by drilling		Diminution if any.					
		Port.	Std.	Port.	Std.		port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
SPAR SHEER STRAKE <i>M</i>	72	75	63	-	09	46	51	51	-	-	46	46	51	-	-	<i>Drilled plates renewed under- lined in Red.</i>			
Strake below <i>L</i>	"	67	67	05	05	50	51	51	-	-	50	51	51	-	-				
MAIN SHEER STRAKE <i>K</i>	"	59	59	13	13	"	67	51	-	-	"	51	51	-	-				
1st Strake below <i>J</i>	"	55	67	17	05	"	67	55	-	-	"	46	51	04	-				
2nd " <i>H</i>	"	59	55	13	17	"	67	55	-	-	"	39	42	11	08	<i>229 dull plate</i>  <i>2020</i> <i>Lloyd's Register</i>			
3rd " <i>G</i>	"	59	59	13	13	"	51	51	-	-	54	46	46	08	08				
4th " <i>F</i>	"	67	67	05	05	56	67	67	-	-	72	54							
5th " <i>E</i>	"	59	59	13	13	72					68								
6th " <i>D</i>	"	67	63	05	09	"					72	54							
7th " <i>C</i>	"	67	67	05	05	72	52	67	63		72	52	59	59					
8th " <i>B</i>	"	67	63	05	09	"	67	67			72	56	59	63					
9th " <i>A</i>	"	63	67	09	05	72	67	67			72	54	67	67					
KEEL	"	71				"	67				72								

Drillings at ends to be made in the vicinity of the peak bulkheads.

004382-004386-0129

Lloyd's Register  
Foundation