

Lloyd's Register of Shipping.

Order: 5629.

(Report on Machinery, No. Port)

No. 22616

ENGINE FORGINGS ~~OR CASTINGS~~.

I have to report that the ~~XXXXXX~~ Steel Forgings ~~XXXXXX~~, as herein described, manufactured by **Messrs. Bochumer Verein** of **Bochum** for the Engines No. being constructed by **Messrs. G. Seebeck A.G.** of **Wesermünde** for the Ship No., being built by of

have been inspected by me as set forth below, and found to be, so far as can be seen, **3 cross heads, 3 piston rods, 6 excentric rods and 3 link blocks sound and free from surface defects.-**


on Forgings or Castings.

Lloyd's

Düsseldorf 6th November 1925.

No. 6250/6253/6254/6255/6249/6257.

M.B.5.11.25.



	XXXXXX			STRAIGHT SHAFTING.			
	3 piston rods			3 cross heads	6 excentric rods	3 link blocks	
	6253/6254/6255			6250	6249	6257	
Material* ...	Annealed			Siemens	Martin	Ingot	Steel
How made ...	forged			forged	forged	forged	
Dimensions ...	80mm Ø						
Progress on Inspection }	rough turned			rough turned	rough turned	rough turned	
Tests on Standard Test Pieces.	.798	3"		.798	3"		.798 3"
Tensile Test—	29,5	29,9	29,4	30,7	31,6	31,3	
Tons per square inch	34,5	34,5	36,5	33,8	30,5	30,5	
Extension per cent	180 degr. good			180 degr. good	180 degr. good	180 degr. good	
Angle before fracture	180 degr. good			180 degr. good	180 degr. good	180 degr. good	
Dates when Inspected	5.11.25.			5.11.25.	5.11.25.	5.11.25.	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at **Düsseldorf.**

* If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.


on 10.20. T.

† State if annealed



904621-004629-0226

594/5



© 2020

Lloyd's Register Foundation