

For the information of Surveyors and the Committee only.

Received at

Office,

190

# K. Lloyd's Register of British & Foreign Shipping.


(Report on Vessel No.

Port

Order 32319.

No. 1367

## SHIP FORGINGS OR CASTINGS.



I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by Aktien Gesellschaft Fried. Krupp Stahlw. Annen of Annen, Westfalia for the Vessel No. 249, being built by Messrs. Joh. C. Tecklenborg A.G. of Geestemünde have been inspected by me as set forth below and found to be, so far as can be seen, sound and free from defects.

1 Sternframe in two parts, 1 Stem bottompart.

Düsseldorf 14th December 1911.

*Th. H. H. H.*

Lloyd's

No. 88,89.

K.12.11.

	STERN FRAME.	RUDDER FRAME.	STEM.
Material*	Annealed S.M. Steel		Annealed S.M. Steel
How made	Cast		Cast
Dimensions	10 3/4" x 8"		10 1/2" x 2 3/4"
Progress on Inspection	rough & finished		rough & finished
Date when Inspected	13. & 30. 11. 1911.		18. 11. 1911.
	13. 12. 1911.		13. 12. 1911.

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS, OR PARTICULARS OF TESTS APPLIED TO CASTINGS.

Sternframe top part	32,4 Tons per square inch	26,2% Elong. in 3"
	31,5 - - - -	26,2% - - -
Sternframe bottom part	32,5 - - - -	25,0% - - -
	33,2 - - - -	22,4% - - -
1 Stem bottom part	31,4 - - - -	26,2% - - -
	31,8 - - - -	26,2% - - -
diameter of sample .798"		

Percussive and bend tests good.

Fee (if any chargeable) £

To be paid at Düsseldorf

\* If of Iron, state whether scrap or puddled Iron.