

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19__

Lloyd's Register of Shipping.

(Report on Machinery, No. 9387 Port TRIESTE)

No. 205 ENGINE FORGINGS OR CASTINGS

I have to report that the ~~Forgings or Castings~~ as herein described, manufactured by Cantieri Navali e Officine Meccaniche of Venice for the Engines No. _____ being constructed by Cant. Nav. e Offic. Mecc. of Venice for the Ship No. 74, being built by Cantieri Navali e Officine Meccaniche of Venice have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Cant. Nav. e Officine Mecc., Venice.

on Forgings ~~or Castings~~

Lloyd's

Trieste, 28th August 1931.

No. 205
AC 12.8.31

Alfred Bee

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			Two SCREW SHAFTS
Material				S.M. steel
Made				forged
Heat-treated				yes
Dimensions, Forgings				195 m/m diam.
Material, Castings				
Test on { Inspection }				forged & finished
Test on Standard Test Pieces.				
Test— Tensile per square inch				20.4
Elongation per cent				30.0
Bending Test— Time before fracture				180° good
When Inspected				24.2.31 at Prague 17.3.31 - 12.8.31 at Venice.

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

130.