

Lloyd's Register of Shipping

Comm. No: 2445/W
Order: 3959/1055


No: 2759

Surveyors' Office, VIENNA.


is to certify, that **John Stanley Helyer** the undersigned surveyor to this Society tested in
works of **Messrs. Witkowitz Bergbau & Eisenhütten Gew** of **Witkowitz**
annealed Siemens Martin Boiler steel **plates** specified hereunder, ordered
Messrs. Cantieri Navali ed Officine Meccaniche di of **Venezia**
the ship No. **74** Boiler No. **56/57** **Venezia**
and that the results of tests were as are set forth below.

Dimensions. in millimeters			Intended for	Sample number	Charge- number	Tensile tenacity in Kg/mm ²			Elongation in 200 mm. in %	Bending tests.		Remarks.
Length.	Breadth.	Thick- ness.				As per rules.	Ord- ered.	By test.		Cold.	Tem- pered	
180	3300	25	Shell plates	349	9303	44	44	47.3	26	g o o d		
"	"	"		C	"	50	50	45.3	24			
"	"	"		350	9331	"	"	48.5	27			
"	"	"		C	"	"	"	46.2	25			
"	"	"		351	"	"	"	49.0	25			
"	"	"	C.C. Plates	C	"	"	"	45.8	23			
300	425	23		352	9303	"	"	47.6	25			
400	"	24		C	"	"	"	45.3	27			
500	1500	20		353	"	"	"	45.3	24			
600	"	"		354	"	"	"	48.6	25			
700	730	16		355	"	"	"	48.4	26			
"	"	"		356	"	47	"	48.7	23			
800	"	"		357	"	47	"	45.9	27			
900	"	"		358	"	"	"	48.6	24			
1000	750	20		359	"	"	"	49.3	27			
1100	"	"		360	"	"	"	48.4	20E			
1200	"	"		361	"	"	"	46.9	29			

Vienna, 13th December 1930



SURVEYOR TO LLOYDS REGISTER



005118-005131-0286

upon the terms of the Rules and Regulations of the Society, which provide that:—
endeavours to ensure that the functions of the Society are properly
are under any circumstances whatever to be held responsible
surveyors, or in any entry in the Register Book or other public
surveyors, or other Officers or Agents of the Society.

strength may not be used in the construction of boiler
per square millimeter. 1 Kilo per square millimeter

© 2020

Lloyd's Register

Foundation