

Lloyd's Register of Shipping.

Komm.No: 35568-Rw 9320
Order: 6649

No: 2 7 6 0
4 1 2 4

Surveyors' Office, VIENNA.

is to certify, that **Heinrich Jung** the undersigned surveyor to this Society tested in works of **Messrs. Witkowitz Bergbau & Eisenhütten Gew.** of **Witkowitz** annealed **Siemens Martin** Boiler steel specified hereunder, ordered **Messrs. Cantieri Navali Officine Meccaniche di Venezia** of **Venezia** the ship No. **74** Boiler No. **56/57** and that the results of tests were as are set forth below.

Dimensions. in millimeters			Intended for	Sample number	Charge- number	Tensile tenacity in kg/mm ²			Elongation in 200 mm. in %	Bending tests.		Remarks
Length.	Breadth.	Thick- ness.				As per rules.	Ord- ered.	By test.		Cold.	Tem- pered	
950-050	2600	12	Morison-furnaces	363	9322	41	41	41.8	26	g o o d		No:3405/6
"	"	"	"	364	"	47	47	43.0	29	"		No:3407
000	1200ins.	15	steam dome	365	"	"	"	42.3	29	"		No:3408

V i e n n a, 13th December 1930

H. Jung
SURVEYOR TO LLOYDS REGISTER



This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—

While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society.

—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0.635 Tons per square inch.

005118-005131-0288