

*Cabo Delgado*  
**TRIESTE** Rpt 9387

# Lloyd's Register of Shipping.

Komm. 35568-Rw

Order: 6649

No: 2756  
 2699

Surveyors' Office, VIENNA.

is to certify, that **John Stanley Helyer** the undersigned surveyor to this Society tested in works of **Messrs. Witkowitz Bergbau & Eisenhütten Gew.** of **Witkowitz** annealed Siemens Martin Boiler steel specified hereunder, ordered by **Messrs. Cantieri Navali e Officine Meccaniche** of **Venezia** the ship No. **74** Boiler No. **56/57** and that the results of tests were as are set forth below.

Dimensions in millimeters			Intended for	Sample number	Charge-number	Tensile tenacity in Kg/mm <sup>2</sup>			Elongation in 200 mm. in %	Bending tests.		LLOYDS 2699 Remarks. VSH.5.12. 1930
Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered	
1000	1050	12	corrugated furnaces	362	9322	41	41	41.9	29	g o o d	No: 239/40	
"	"	"	"	364	"	47	47	43.0	29	"	No: 241	
1000	1200 ins. ø	15	steam dome	365	"	"	"	42.3	29	"	No: 242	

V i e n n a, 9th December 1930

*J. S. Helyer*

SURVEYOR TO LLOYD'S REGISTER



This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—  
 "While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society."  
 N.B.—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0,635 Tons per square inch.