

REC'D NEW YORK APR 25 1927

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_

# Lloyd's Register of Shipping.

(Report on Machinery, No. 378 Port Cleveland).

## No. 965 ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel~~ Forgings or Castings, as herein described, manufactured by Amer. Ship Bldg Co. of Lorain Ohio for the Engines No. 794 being constructed by Amer S.B.Co. of Lorain Ohio for the Ship No. 794, being built by Amer Ship Bldg Co. of Lorain Ohio have been inspected by me as set forth below, and found to be, so far as can be seen, Sound.


*E. Drummond*  
Cleveland, Ohio

Lloyd's  
No. 965  
Dated 29-1926  
S.D.

	CRANK SHAFT.	STRAIGHT SHAFTING.		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
Material		<u>OK. Steel</u>		
Condition		<u>Forged</u>		
Conformity		<u>to approved drawings</u>		
Finish		<u>Rough &amp; machined</u>		
Standard Pieces.	<u>42000</u>	<u>69600</u>		<u>67600</u>
Estimated weight square inch	<u>68800</u>	<u>68000</u>		<u>68400</u>
Percentage	<u>31.9</u>	<u>34.3</u>		<u>34.3</u>
Winding Test	<u>180°</u>	<u>180°</u>		<u>180°</u>
More fracture	<u>180°</u>	<u>180°</u>		<u>180°</u>
When Inspected	<u>Nov 9 etc.</u>	<u>Nov 9 etc.</u>		<u>Nov 9 etc.</u>

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:-

(if any chargeable) £  
To be paid at



If iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

105644-005655-0045