

# Lloyd's Register of Shipping.

(Report on Vessel No. 9788 Port Gothenburg)

The words FORGINGS or CASTINGS, IRON or STEEL, should be struck out as may be required.

## No. 2476 SHIP ~~FORGINGS~~ CASTINGS.

I have to report that the undermentioned ~~Steel~~ ~~Forgings~~ ~~Castings~~, manufactured by Messrs. A.-B. Lindholmen-Motala of Motala Verkstad for the Vessel No. 461, being built by Messrs. A.-B. Götaverken of Gothenburg have been inspected by me as set forth below and found to be, so far as can be seen, sound and free from defects.

Mark on ~~Forgings~~ Castings.

Lloyd's  
No. 8714-15  
VB 1.4.31

Gothenburg, 7th April, 1931,

*V. Paulow*


One shaft bracket. One shaft bracket.

	<del>STEEL</del> <del>IRON</del> <del>CASTINGS</del>	<del>STEEL</del> <del>IRON</del> <del>CASTINGS</del>	STEM.
Material* ...	S.M. Steel	S.M. Steel	/
How made ...	Cast	Cast	
If annealed ...	Yes	Yes	
Dimensions ...	As per plan.	As per plan.	
Progress on Inspection ...	Cast	Cast	
Date when Inspected ...	1.4.31.	1.4.31	
CASTINGS. Tests on Standard Test Pieces.	No.8714	No.8715	
Tensile Test— Kgs per square mm.	45.5	48.6	
Extension per cent. ...	36.0	33.0	
Cold Bending Test— Angle before fracture	120° good.	120° good.	
Drop Test— Height from ground ...	good 11'-0"	good 11'-0"	
Hammering Test— If made according to Rules and found satisfactory ...	Good.	Good.	

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £ --- : :

To be paid at GOTHENBURG



\* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.