

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19\_\_

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

No. 5397.

## ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel Forgings or Castings~~, as herein described, manufactured by Messrs. Burmeister & Wain of Copenhagen for the Engines No. ✓ being constructed by ✓ of ✓ for the Ship No. 206, being built by Messrs. Bugens Mekaniiske Værksted of Bergen have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects.  
3 piston rods.

Forgings or Castings.

Lloyd's  
No. 6986.  
9.2.24.

Copenhagen, 1<sup>st</sup> April 1924.


S. Clausen.  
SURVEYOR TO LLOYD'S  
REGISTER OF SHIPPING

| 3 Piston Rods.<br>CRANK SHAFT. |                          | STRAIGHT SHAFTING. |                      |                  |
|--------------------------------|--------------------------|--------------------|----------------------|------------------|
|                                |                          | THRUST SHAFT.      | INTERMEDIATE SHAFTS. | PROPELLER SHAFT. |
| ...                            | Annealed S. W. 2. Steel. |                    |                      |                  |
| ...                            | Hydraulic forged.        |                    |                      |                  |
| ...                            | Diam. 4 1/8"             |                    |                      |                  |
| ...                            | Partly rough machined.   |                    |                      |                  |
| ...                            |                          |                    |                      |                  |
| Standard<br>pieces.            |                          |                    |                      |                  |
| St-<br>quare inch              | 34.8                     |                    |                      |                  |
| per cent                       | 31.9                     |                    |                      |                  |
| ng Test                        | good.                    |                    |                      |                  |
| re fracture                    |                          |                    |                      |                  |
| Inspected                      | 4/2, 6/2, 7/2. 24.       |                    |                      |                  |

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

if any chargeable) £1. 40.~  
to be paid at Copenhagen.

iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.



© 2020

Lloyd's Register  
Foundation

005481-005444-0133