

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 10

# Lloyd's Register of Shipping.

der: 677275  
601/  
677264. (Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

No. *14680* ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the ~~Forgings or Castings~~ as herein described, manufactured by Messrs. Humboldt-Deutzmotoren A.G. of Köln - Kalk for the Engines No. \_\_\_\_\_ being constructed by Messrs. Humboldt-Deutzmotoren A.G., Werk Deutz of Köln - Deutz for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Köln - Deutz

or castings or Castings.

Lloyd's

No. *15474*.

H. *29.6.34*.

*Düsseldorf 9th July 1934.*

*Paul Hantz*

|                                  | <del>CRANK SHAFT</del>           | THRUST SHAFT. | INTERMEDIATE SHAFT. | TUBE SHAFT.  |
|----------------------------------|----------------------------------|---------------|---------------------|--------------|
|                                  | <del>KEYWHEEL SHAFT</del>        |               |                     | SCREW SHAFT. |
| ...                              | 1 three throw solid crank shaft  |               |                     |              |
| ...                              | Annealed Siem. Mart. Ingot Steel |               |                     |              |
| ...                              | forged                           |               |                     |              |
| ...                              | Yes                              |               |                     |              |
| as, Forgings                     |                                  |               |                     |              |
| da castings                      |                                  |               |                     |              |
| on }<br>on }<br>Standard Pieces. | rough turned                     |               |                     |              |
| est—<br>square inch              | .788 3"                          |               |                     |              |
| n per cent                       | 35.6                             |               |                     |              |
| ding Test—<br>fore fracture      | 28.0                             |               |                     |              |
| en Inspected                     | 180 degr. good                   |               |                     |              |
|                                  | 29.6.34                          |               |                     |              |

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

f: material has been ordered to special requirements.—

any chargeable) £

To be paid at Düsseldorf.

f wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

006160-006174-0080

© 2020

Lloyd's Register Foundation