

These castings for Hull #974,
Westinghouse Co's. H.P. Turbine #7689, L.P. #7709.

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL.

made by The American Bureau of Shipping.

The Pensacola Shipbuilding Company, Pensacola, Fla.

By	Marks			How		Description		Lbs. # per square inch.	Extension in 8 ins. %	Bend
	Batch #	Test #	Charge Mark	Matl. Thickness	Made By	Area #	Tons Total			
Steel	A.B. #761.			O.H.	Cast	H.P. Spindle	67820	29.0	120°	
gs Co.,	5-29-18.E.S.K.			Steel		Coupling End				
burgh, Pa.										
Do	A.B. #1005.			Do	Do	H.P. Spindle	75580	29.5	120°	
	9-30-18.W.G.T.					Thrust End				
Do	A.B. #711			Do	Do	L.P. Spindle	74200	28.5	120°	
	5-4-18.P.H.C.					Coupling End				
Do	A.B. #386			Do	Do	L.P. Spindle	76800	27.0	120°	
	5-4-18.					Thrust End				
Do	A.B. #773.			Do	Do	L.P. Spindle	69610	29.5	120°	
	5-29-18.					Body				

Accompanying Pittsburgh Machinery Report #100.

J. Hodge

Surveyor to Lloyds Register

MAR 5 - 1920

Pittsburgh, Pa.



© 2021

Lloyd's Register
Foundation

006412-006422-0236