

Lloyd's Register of Shipping.

(Report on Machinery, No. Port

No. 796 ENGINE FORGINGS ~~OR CASTINGS~~.

I have to report that the ~~Iron or~~ Steel Forgings ~~or Castings~~, as herein described, manufactured by Pacific Construction & Eng'g Co of Seattle W. for the Engines No. being constructed by of for the Ship No. 76, being built by Munn & Co. Eng'g Co. of Seattle W. have been inspected by me as set forth below, and found to be, so far as can be seen

Sound & Free from Defect.

Forgings or Castings.

Lloyd's

See Below

Asst

Seattle W.

	CRANK SHAFT.	STRAIGHT SHAFTING.		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
			<u>3</u>	
			<u>Steel Sh.</u>	
			<u>Forged</u>	
			<u>as Req'd.</u>	
			<u>Rough</u>	
Standard Pieces.				
Weight - square inch.		<u>63320</u>	<u>63640</u>	<u>63560</u>
Strength - per cent		<u>31.5</u>	<u>33.5</u>	<u>32.0</u>
Strength Test - per fracture		<u>180°</u>	<u>180°</u>	<u>180°</u>
Inspected		<u>4-12-19</u>	<u>10-12-19</u>	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:-

Lloyd's
No. 796
4-12-19
Ch.

Lloyd's
No. 807
10-12-19
Ch.

Lloyd's
No. 809
10-12-19
Ch.

(if any chargeable) Charged to be paid at Seattle W.

If iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

C. Co.