

E.

# Lloyd's Register of British & Foreign Shipping.

(Report on Machinery, No.

Port

Order 60445/60397/60493.

No. 15903.

ENGINE FORGINGS OR CASTINGS

141

I have to report that the ~~XXXXXX~~ Steel Forgings ~~XXXXXX~~, as herein described, manufactured by Messrs. Haniel & Lueg of Düsseldorf-Grafenberg for the Engines No. C 2123. being constructed by North Eastern Marine Eng. Co, Ltd of W a l l s e n d for the Ship No. , being built by

of have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects.

1 Intermediate shaft

Mark on Forgings or Castings.

Lloyd's

No. 2406

M.B. 12.12.

Düsseldorf 19th. December 1912.

*M. Berg*


	CRANK SHAFT.	STRAIGHT SHAFTING.		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
Material* ...			annealed Siemens Martin Ingotsteel	
How made ...			forged	
Dimensions ...			14 1/8" diam.	
Progress on { Inspection }			rough turned diameter .798"	
Tests on Standard Test Pieces.				
Tensile Test— Tons per square inch ...			28.7	
Extension per cent ...			35.2	
Cold Bending Test— Angle before fracture ...			180 degr. good.	
Dates when Inspected			9. & 18/12. 1912.	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at Düsseldorf

\* If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open-Hearth process.



© 2021

Lloyd's Register

Foundation