

SSEL'S NAME

S/S. BOSNIA.


Report

FIVE No. 254.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in $\frac{9}{20}$ of an inch.

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
NO. 1 B.O. & B.A.D. MAIN SHEER STRAKE	5.5	5.5	5.5	-	0.5	5	5	5	-	-	5	5	5	-	-	
Strake below	5.5	5.5	5.5	-	-	5	5	5	-	-	5	5	5	-	-	
MAIN SHEER STRAKE I	11	11	10.5	-	0.5	8	8	8	-	-	8	8	7	-	1	
1st Strake below	H	6	5	6	1	-	5	5	5.5	-	5	5	5	-	-	
2nd	G	7	6	6.5	1	0.5	6	6	7	-	6	6	6	-	-	
3rd	F	6	6	5.5	-	0.5	5	5	5	-	5	5	4.5	-	0.5	
4th	E	8	6.5	7	1.5	1	7	7	6	-	7	7	7	-	-	
5th	D	7	7	7	-	-	6	5	5.5	1	0.5	6	5	6	1	-
6th	C	7	Zent				6	Zent				6	Zent			
7th	B	6	4				5	4				5	4			
8th	A	12	.				9	.				9	.			
9th																



2020

Lloyd's Regist

Drillings at ends to be made in the vicinity of the peak bulkheads.

007045-007058-0234