

TESTING & EXPERIMENTING WORKS,
99, SOUTHWARK STREET,
LONDON, S.E. 1.

11th September 1919.

TESTS TO ASCERTAIN THE RESISTANCE TO THRUST OF

four-inch cubes of concrete received from yourself.

DESCRIPTION	WEIGHT	DIMENSIONS	BASE AREA	CRUSHING STRENGTH		
				TOTAL	PER SQ. INCH	PER SQ. FOOT
Age 28 days.	LBS.	INCHES	SQ. INS.	LBS.	LBS.	TONS
Marked 13. 8. 19	5.16	4.00 4.00 x 4.00	16.00	57,400	3590	230.8
Proportions do. (3/4 Foreshore Ballast do. Sand.						
do. 'Sussex' Brand Mr. W.H. Adams letter of 16 th Aug. '19)	5.23	4.00 4.00 x 4.06	16.24	60,300	3770 - 3500	242.4 - 225.0
do.	5.21	4.00 4.00 x 4.06	16.24	50,300	3140	201.9

Mr. Mehr Esq.

47 Bowley Street, Westminster, S.W. 1.

David Kirkaldy & Son



© 2021

Lloyd's Register
Foundation

007246-007256-0352