

On the (State if Machinery fitted Aft and of Single, Twin or Triple Screw)

Steel Single Screw Motorship KIRISHIMA

Rpt. 7.

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19

Lloyd's Register of Shipping.

Order: 92521. (Report on Machinery, No. _____ Port _____) **DUPLICATE.**

No. 31544 ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Haniel & Lueg of Düsseldorf for the Engines No. H 393 being constructed by Messrs. Deutsche Werft of Hamburg for the Ship No. _____, being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Hamburg.

rk on Forgings or Castings.

Lloyd's
No. 1984.
F.K. 6.8.30.

Düsseldorf 7th August 1930.

F. Rollmann

| | CRANK SHAFT | THRUST SHAFT. | INTERMEDIATE SHAFT. | TUBE SHAFT. |
|--------------------------------|----------------------------------|---------------|---------------------|--------------|
| | 1 thrust shaft | | | |
| | KEYWAY SHAFT | | | SCREW SHAFT. |
| Material* ... | Annealed Siem. Mart. Ingot Steel | | | |
| How made ... | forged | | | |
| Annealed ... | Yes | | | |
| Dimensions, Forgings | 436 mm Ø | | | |
| Weight, Castings | | | | |
| Progress on { Inspection } | rough turned | | | |
| Tests on Standard Test Pieces. | .798 3" | | | |
| Tensile Test— | 28.7 | | | |
| Tons per square inch | | | | |
| Extension per cent | 33.8 | | | |
| Old Bending Test— | | | | |
| Angle before fracture | 180 degr. good | | | |
| Dates when Inspected | 6.8.30. | | | |

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

10m.10.30.

007474-007485-0101

Angles ...

Pool Deck, Angle, F or F