

S.S. Soyo Maru
Lloyd's Register of Shipping,

(MEIKAI BUILDING)

32, AKASHI-MACHI,

KOBE, 8th. August 1930.

2590.

This is to Certify that at the request

of The Kobe Steel Works, Ltd., Kobe,

Hearth Steel Forgings or Castings named below ~~were~~ ^{has} ~~were~~ examined and their works on 25th. November 1929 to 26th. July 1930.

and to be as far as could be ascertained, sound and free from defect.

(7) Sets Cast Steel Cross-head pin Brasses. 320 m/m dia.

Examined in finished condition.

and Dropped from a height of 8 feet on to a steel slab,

suspended and hammered without indication of defect.

Test Mark	Tenacity Tons/sq in	Elongation % in 2"	Bend 1" x 1/4" x 120°
60 A	30.3	28	Good
63 C	31.5	26	"
63 D	30.2	29	"
63 E	29.0	30	"
70 D	30.3	27	"

Continued on sheet 2.

The castings are intended for Asano Dockyard Ship No.270

and ~~has~~ ^{has} ~~have~~ been stamped as follows:-


TEST MARKS AS ABOVE
 LLOYD'S
 No. 2590
 22-7-30
 A.D.M. LR

Yen 49.00

A.D. Morrison

Surveyor to Lloyd's Register.

... certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—
 ... the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be
 ... that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy
 ... or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the
 ... any error of judgment, default, or negligence of the Surveyors, other Officers or Agents of the Society."



Lloyd's Register
 Foundation

007553-007562-0244 1/2

Lloyd's Register

Sheet No. 2.

Kobe, 8-8-30.

ificate No. 2590.

st Mark	Tenacity Tons/sq. in.	Elongation % in 2"	Bend 1" x $\frac{3}{4}$ " x 120°
70 E	31.6	27	Good
70 F	30.1	27	"
46 D	31.0	28	"
46 E	30.9	28	"
473 E	30.4	26	"
473 F	29.9	27	"
473 G	31.0	28	"
473 H	31.6	27	"
370 C	33.9	27	"

A. Morrison

SURVEYOR TO LLOYD'S REGISTER.



© 2020

Lloyd's Register
Foundation

0244%