

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19

Lloyd's Register of Shipping.

(Report on Machinery, No. _____ Port _____)

No. 296. ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Mitsubishi Zosen Kaisha, Ltd.. of Nagasaki. for the Engines No. 474 being constructed by Messrs. Nagasaki Works, of Mitsuboshi Zosen Kaisha, Ltd.. for the Ship No. 474, being built by them, of _____ have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. ~~These have been despatched to~~ 14 Intermediate Shafts.

K. Kishigami & Anderson

NAGASAKI. 20th Oct 1930.

Forgings ~~or Castings~~

Lloyd's

No. 296. *B*

28/6/30
10/7/30
8/10/30
6/16/25-8-30.

	CRANK SHAFT.	TRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLY WHEEL SHAFT.			SCREW SHAFT.
...			Ingot steel	
e ...			Forged	
ed ...			Yes	
ns, Forgings			350 m/m	
Castings			/	
on {			Forged, rough turned & Finished.	
tion {				
Standard	Test Mark:-	TN 2. 3. 4. 5. 6. 7. 8. 9. 10.		
Pieces.	Ten.	30.8 28.8 28.4 28.4 29.2 30.0 32.0 30.8 28.4		
est-	Elon.	33.8 38.0 37.9 35.5 38.0 36.0 36.0 37.0 38.2		
square inch	Test Mark:-	TN 11. 12. 13. 14. 15.		
	Ten.	30.4 30.0 28.0 29.6 28.4		
a per cent	Elon.	25.9 37.8 37.5 35.7 35.8		
ding Test-			180°	
fore fracture			without fracture	
en Inspected			4-4-30 to 25-8-30.	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:-

any chargeable) £

To be paid at

wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.