

For the information of Surveyors and the Committee only.

Received at NAGASAKI Office. MAR 31 1930

Lloyd's Register of Shipping.

Order: 15892/st
 Post: 24052 (Report on Machinery, No. _____ Port _____)
 Best: 5761

No. 2151 ENGINE FORGINGS OR CASTINGS. ~~XXXXXXXXXXXX~~

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Witkowitz Bergbau & Eisenh. Gew. of Witkowitz for the Engines No. _____ being constructed by (474) of _____ for the Ship No. 475, being built by Messrs. Mitsubishi Shoji Kaisha of Nagasaki have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Messrs. Mitsubishi Shoji Kaisha of Nagasaki

Report on Forgings ~~or Castings~~

Vienna, 12th March 1930

Lloyd's
 No. 3969 10350
HK.8.3.30

Star

Hans Kolbow

	1 three throw CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	KEYWAY BECK SHAFT			SCREW SHAFT.
Material* ...	<u>S.M. Ing. Steel</u>			
made ...	<u>forged</u>			
annealed ...	<u>annealed</u>			
Dimensions, Forgings	<u>470 Ø</u>			
Weight, Castings	<u>---</u>			
Process on inspection }	<u>finished</u>			
Tests on Standard Test Pieces.				
Tensile Test—	<u>30.5 31.5</u>			
Stress per square inch				
Elongation per cent <u>3"</u>	<u>33.6 34.9</u>			
Bending Test—	<u>180 degrees good</u>			
Angle before fracture				
Date when Inspected	<u>8.3.1930</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at VIENNA

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

