

Received at _____ Office, _____ 19__

Lloyd's Register of Shipping.

(Report on Machinery, No. _____ Port _____)

No. 208 ENGINE FORGINGS OR ~~CASTINGS~~.

I have to report that the Iron or Steel Forgings or Castings, as herein described, manufactured by Bethlehem Steel Co. of Pittsburgh, Pa. for the Engines No. — being constructed by Lodd Dry Dock & Repair Co. of Lacoma, Wash. for the Ship No. —, being built by Same of Same have been inspected by me as set forth below, and found to be, so far as can be seen, Sound.

The words FORGINGS or CASTINGS, IRON or STEEL, should be struck out as may be required.

LLOYD'S No. <u>210</u> <u>7-1-19</u> W.H.	LLOYD'S No. <u>210</u> <u>13-1-19</u> W.H.	LLOYD'S No. <u>211</u> <u>7-1-19</u> W.H.	LLOYD'S No. <u>212</u> <u>7-1-19</u> W.H.	LLOYD'S No. <u>213</u> <u>7-1-19</u> W.H.	LLOYD'S No. <u>215</u> <u>7-1-19</u> W.H.
--	---	--	--	--	--

Mark on Forgings or Castings.

Lloyd's No. <u>208</u> <u>13-1-19</u> W.H.	LLOYD'S No. <u>217</u> <u>13-1-19</u> W.H.
---	---


William Holme (33)
Pittsburgh, Pa.

	CRANK SHAFT.		STRAIGHT SHAFTING.					
			THRUST SHAFT.	INTERMEDIATE SHAFTS.			PROPELLER SHAFT.	
Material	<u>O.H. Steel</u>							
How made	<u>Forged.</u>							
Dimensions								
Progress on Inspection	<u>Forged and Rough turned</u>							
Tests on Standard Test Pieces.	<u>208</u>	<u>210</u>	<u>210</u>	<u>211</u>	<u>212</u>	<u>213</u>	<u>215</u>	<u>217</u>
Tensile Test— Tons per square inch	<u>68480</u>	<u>66960</u>	<u>66960</u>	<u>70800</u>	<u>68100</u>	<u>66560</u>	<u>68120</u>	<u>69170</u>
Extension per cent	<u>30.5</u>	<u>30.0</u>	<u>30.0</u>	<u>30.0</u>	<u>33.0</u>	<u>29.0</u>	<u>30.0</u>	<u>31.0</u>
Old Bending Test— Angle before fracture	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>
Dates when Inspected	<u>From 7-1-19 to 13-1-19</u>							

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee \$130⁰⁰
Each \$12⁰⁰

Fee (if any chargeable) £ _____
To be paid at Pittsburgh.



© 2020

Lloyd's Register Foundation

* If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.