

For the information of Surveyors and the Committee only.

Received at NAGASAKI Office, FEB 14 1930

Lloyd's Register of Shipping.

Order: 15892/St
Post: 24052
Best: 5761

(Report on Machinery, No. 1750 Port Nag)

No. 1991 ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the Forgings ~~as castings~~, as herein described, manufactured by Messrs. Witkowitz Bergbau & Eisenh. Gew. of Witkowitz for the Engines No. being constructed by of for the Ship No. 473, being built by Messrs. Mitsubishi Shoji Kaisha of Nagasaki have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Messrs. Mitsubishi Shoji Kaisha of Nagasaki

on Forgings ~~as castings~~

Vienna, 25th January 1930

Lloyd's
No. 3901 10173 Port
HK. 10.1.30

Hans Kollow.

	1 three throw solid			
	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
				SCREW SHAFT.
Material* ...	EXAMINED SHAFTS			
made ...	<u>S.M. Ing. Steel</u>			
nealed ...	<u>forged</u>			
ensions, Forgings	<u>annealed</u>			
ht, Castings ...	<u>470 g</u>			
ress on } spection }	<u>finished</u>			
as on Standard Test Pieces.				
lle Test—				
ns per square inch ...	<u>30.0 30.6</u>			
tension per cent ...	<u>33.6 34.9</u>			
Bending Test—				
gle before fracture ...	<u>180 degrees good</u>			
s when Inspected	<u>6.12.29; 10.1.30</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at VIENNA

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

Lloyd's Register
Foundation

607825-007833-0156
607825-007833-0157