

For the information of Surveyors and the Committee only

Received at NAGASAKI. Office, JAN 6 1930

Lloyd's Register of Shipping.

Number: 15892/St
 Port: 24052 (Report on Machinery, No. 1750 Port Nag)
 Date: 5761

No. 1875 ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~are Castings~~, as herein described, manufactured by Messrs. Witkowitz Bergbau & Eisenhütten Gew of Witkowitz for the Engines No. _____ being constructed by Messrs. Mitsubishi Shoji Kaisha of Nagasaki for the Ship No. 472, being built by 473

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Messrs. Mitsubishi Shoji Kaisha of Nagasaki

Vienna, 9th December 1929

Lloyd's

No. 3860 10085
5.12.29

Hans Kolbow

	1 three throw solid CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
				SCREW SHAFT.
Material	<u>S.M. Ing. Steel</u>			
Condition	<u>forged</u>			
	<u>annealed</u>			
Dimensions, Forgings	<u>470 Ø</u>			
Castings	<u>finished</u>			
Test— Tensile strength per square inch	<u>31.2</u> <u>31.1</u>			
Reduction of area per cent	<u>31.6</u> <u>34.2</u>			
Enduring Test— before fracture	<u>180 degrees good</u>			
When Inspected	<u>1.11; 5.12.29</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

© 2020
 VIENNA

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

Lloyd's Register
 Foundation

007825-007833-0158