

Rpt. 7.

For the information of Surveyors and the Committee only.

Received at

NAGASAKI

Office,

JAN 27 1930

Lloyd's Register of Shipping.

Order: 15892/St
Post: 24052
Best: 5761

(Report on Machinery, No. 1750 Port Nag)

No. 1910 ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Witkowitz Bergbau & Eisenh. Gew. of Witkowitz for the Engines No. being constructed by of for the Ship No. 473, being built by Messrs. Mitsubishi Shoji Kaisha of Nagasaki have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Messrs. Mitsubishi Shoji Kaisha of Nagasaki

Mark on Forgings ~~or Castings~~

Vienna, 30th December 1929

Lloyd's

No. 3864

10100

HK.18.12.29

Hans Kolbow.

1 three throw solid

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	CRANK SHAFT.			SCREW SHAFT.
Material* ...	S.M. Ing. Steel			
How made ...	forged			
If Annealed ...	annealed			
Dimensions, Forgings	470 Ø			
Weight, Castings	---			
Progress on { Inspection }	finished			
Tests on Standard Test Pieces.				
Tensile Test— Tons per square inch ...	29.0 28.8			
Extension per cent ...	36.2 32.9E			
Cold Bending Test— Angle before fracture ...	180 degrees good			
Dates when Inspected	28.11; 18.12.29			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at

VIENNA

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

10m.3.29.

t. 10). 10m.3.29.

007825-007833-0182

Working pressu