

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19

Lloyd's Register of Shipping.

(Report on Machinery, No. 1750 Port Nag)

No. 275. ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Mitsubishi Zosen Kaisha, Ltd.. of Nagasaki. for the Engines No. 473 being constructed by Messrs. Nagasaki Works, of Mitsubishi Zosen Kaisha, Ltd.. for the Ship No. 473, being built by them.

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. ~~These have been despatched to~~

14 Intermediate Shafts.

Forgings ~~or Castings~~

K. Kishigami *Gundersen*

NAGASAKI. 1st October 1930.

Lloyd's

No. 275.
4/7/10-4-30.
7/10-5-30.
10/26-6-30.

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			SCREW SHAFT.
			Ingot steel	
			Forged	
			Yes	
			350 m/m	
			-	
			Forged, rough turned and Finished.	
Test Mark:-	TN 1. 3. 4. 5. 6. 7. 8. 9. 10.			
Ten.	30.4 28.0 28.8 28.4 28.8 28.8 29.2 28.8 28.8			
Elon.	38.5 39.5 38.2 37.8 34.6 41.1 37.7 40.5 38.0			
Test Mark:-	TN 11 12. 13. 14. 15.			
Ten.	29.2 30.4 31.2 30.8 28.8			
Elon.	38.0 37.9 37.7 38.8 38.0			
in per cent			180°	
ding Test:-	-			
More fracture				
en Inspected			21-2-30 to 26-6-30.	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:-

any chargeable) £

To be paid at

of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

© 2020

Lloyd's Register
Foundation

007825-007833-0163