

Lloyd's Register of Shipping.

Order: 2592022
Post: 2916.

(Report on Vessel No. 7286 Port Trieste)

No. 1434. SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by Messrs. Wittk. Bergl. u. Eisenh. Gewerkschaft of Witkowitz for the Vessel No. 157, being built by Messrs. Carli. Navale Triestino of Moufalcone have been inspected by me as set forth below and found to be, so far as can be seen, 1 cast stem shoe, sound and free from defects.

Mark on Forgings or Castings.

Lloyd's
No. 1434. 1.
E.F. 6.3.25.

Vienna, 23rd March 1925.


Edward Faindyz

	STERN FRAME.	RUDDER FRAME.	STEM. Shoe	
Material*	/	/	Am. Iron. Mark. Steel	
How made			cast	
Dimensions			No sketch	
Progress on Inspection			finished	
Date when Inspected			12.2, 6.3.1925.	
CASTINGS.			No: 1.	
Tests on Standard Test Pieces.				
Tensile Test—				
Tons per square inch			27.7	27.9
Extension per cent. <u>32</u>			33.2	33.8
<u>32</u>	33.6	33.3		
Cold Bending Test—				
Angle before fracture	120 deg. good.			
Drop Test—				
Height from ground	9'			
Hammering Test—				
If made according to Rules and found satisfactory	satisfactory.			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

25 MAR 1925

Fee (if any chargeable) £
To be paid at **VIENNA**



* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.